COLEMAN DESIGNATION

STATISTICS IN CONTRACTOR

tion for an

A DOM STRUCTURE AND

COLOR DATE OF THE PARTY OF THE

GLOTON THE

distriction of the

Otto 2670

Specifications

Content	31% post-consumer recycled polyester 34% pre-consumer recycled polyester 35% polypropylene
Weight	13.5 ± 0.5 oz./lin. yd.
Width	66" min. useable
Repeat	none
Treatment	polyester binder


Cleaning Code

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup.

Acoustical Performance

The plot below summarizes impedance tube measurements of absorption of an anechoic termination and various fabrics in front of the anechoic termination.

Acoustical Performance for Panel Applications (ISO 10534-2)



NRC of anechoic termination	1.00
NRC of fabric in front of anechoic termination	.85







Platinum 7010



Misty 7011



Gold

7020

Straw

7013

7012

Pebble



Slate 7030





Martinet Statistics and

"I'lling Total States of the states of the states have an upply optimistic an distant tion - Hills - An - De and a party THE OF THE PARTY AND A STRUCTURE AND



Patina 7032



PANEL | ACOUSTIC

Performance

₩	Colorfastness to Light (AATCC 16.3 Option 3) Grade 4 min. at 40 hours
0	Colorfastness to Crocking (AATCC 8) Grade 4 min. dry & Grade 3 min. wet
\mathbf{x}	Breaking Strength (ASTM D5034) 200 lbf min. warp and 175 lbf min. fill
*	Flammability (ASTM E84) Class I or A

Miscellaneous

Proudly woven in North America supporting our local communities.

Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric.

Visit guilfordofmaine.com for samples.

rtification Marks owned by the Association for Contract Textiles, Inc