Tweed 2737

Specifications

Content	25% post-consumer recycled polyester 75% pre-consumer recycled polyester
Weight	11.7 ± 1.0 oz./lin. yd.
Width	66" min. useable
Repeat	none


Cleaning Code

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup.

Acoustical Performance

The plot below summarizes impedance tube measurements of absorption of an anechoic termination and various fabrics in front of the anechoic termination.

Acoustical Performance for Panel Applications (ISO 10534-2)



NRC of anechoic termination	1.00
NRC of fabric in front of anechoic termination	.95

-----CONTRACTOR IN THE ------

Bleach White 2766



Stainless 2195



Maize 2768



Leaf 2772



Twinkle

Grey Green

2196

Orange

2767

Spa 2773

2168

Royal Blue 2771



2187



Sage Grass 2186

Concrete

2144



Lipstick 2770





Java 2197









Raspberry 2769








PANEL | ACOUSTIC

Performance

₩	Colorfastness to Light (AATCC 16.3 Option 3) Grade 4 min. at 40 hours
0	Colorfastness to Crocking (AATCC 8) Grade 4 min. dry & Grade 3 min. wet
${\times}$	Breaking Strength (ASTM D5034) 225 lbf min. warp and 175 lbf min. fill
*	Flammability (ASTM E84) Class I or A

Sustainability



Miscellaneous

Proudly woven in North America supporting our local communities.

Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric.

Visit guilfordofmaine.com for samples.

FL

This pattern is included in the underwriters labor required on approved panels from participating manufacturers.

*Certification Marks owned by the Association for Contract Textiles. Inc